

113.80



# PRO-PARK™ WATERBORNE TRAFFIC MARKING PAINT

B97 SERIES

As of 03/01/2013, Complies with:			
OTC	Yes	LEED® 09 CI	Yes
SCAQMD	Yes	LEED® 09 NC	Yes
CARB	Yes	LEED® 09 CS	Yes
CARB SCM 2007	Yes	LEED® 09 H	No
MPI #	97	NGBS	Yes

## CHARACTERISTICS

**PRO-PARK TRAFFIC MARKING PAINT** is a premium quality waterborne acrylic alkyd traffic marking paint. It has excellent chemical and dirt pickup resistance. Pro-Park delivers the performance expected by the most discerning contractor, property manager or national retail chain.

- Apartments Communities
- Shopping Centers
- Schools and Universities
- Municipalities
- Property Managers
- Asphalt Seal Contractors
- Pavement Strippers

The coating may be made into reflective paint by dropping on glass beads while the paint is still wet.

Can be used with stencils (Available through Sherwin-Williams) for street and parking lot marking:

- Directional Arrows
- STOP
- YIELD
- Numbers
- Pedestrian Crossing
- Handicap Markings

White	B97WD2434
Yellow	B97YD2467
Firelane Red	B97RD2012
Blue	B97LD2022
Black	B97BD2021

## SPECIFICATIONS

**Finish:** Flat  
**Colors:** White, Yellow, Blue, Red, Black  
**Volume Solids:** 62 ± 2% (White)  
**Weight Solids:** 77 ± 2% (White)  
**VOC :** <50 g/L; <0.42 lb/gal

As per 40 CFR 59.406 and SOR/2009-264, s.12

### **Recommended Spreading Rate per coat:**

Approximately 330 lineal feet of standard 4" stripe per gallon

**Wet mils (microns)** 15.0 / 375

**Dry mils (microns)** 9.0 / 225

**Coverage sq ft/gal (m<sup>2</sup>/L)** 108 / 2.7

### **Drying Schedule @ 15.0 mils / 375 microns wet, @ 77°F / 25°C, @ 50% RH:**

**Dry-no-pickup:** 30 minutes

**Dry to recoat:** 60 minutes

**Open to heavy traffic:** 120 minutes

**Drying time is temperature, humidity, and film thickness dependent.**

**Shelf Life:** 12 months, unopened

**Store indoors at 40°F / 4.5°C to 100°F / 38°C**

**Flash Point:** 150°F / 65°C, PMCC

**Reducer:** Water

Spreading rates are calculated on volume solids and do not include an application loss factor due to surface profile, roughness or porosity of the surface, method of application, surface irregularities, over-thinning, climatic conditions, and excessive film build.

### **Cured Asphalt, Concrete, and Brick:**

1 ct. Pro-Park Traffic Marking Paint

@ 330 lineal feet of standard 4" stripe per gallon

### **Abrasion Resistance (falling sand)**

Method: ASTM D968

Result: 150 liters

### **Bleed Resistance**

Method: ASTM D969

Result: >0.95 over seal coat

### **Color (yellow)**

Method: Fed. Std. 595 #33538

Result: Pass

### **Dry-No-Pickup**

Method: ASTM D711

Result: <30 minutes @ 77°F/25°C

### **Dry Opacity (Contrast Ratio)**

Method: Fed. Met. 141C at 5 mils (125 microns) wet

Result: 0.95 (white)

### **Flexibility**

Method: ASTM D522, 1/2" mandrel

Result: Pass

### **Reflectance (white)**

Method: ASTM-E97

Result: 85% minimum

### **Scrub Resistance**

Method: ASTM D2486

Result: 500 cycles minimum

**PRO-PARK™**  
**WATERBORNE TRAFFIC MARKING PAINT**



**SURFACE PREPARATION**

**WARNING!** Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.

Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion. Surfaces should be clean and dry and free from loose or peeling paint. Do not apply when air or surface temperatures are below 40°F (4.5°C), or when the relative humidity exceeds 85%, or when the temperature falls below the dew point.

The presence of concrete sealers or efflorescence on new concrete may interfere with adhesion and should be removed by extended weathering, etching, or abrasive blasting.

Most previously painted lines may be repainted without additional surface preparation, provided the old paint is still tightly adhered to the surface. However, multiple layers of paint will eventually peel and require removal.

New asphalt surfaces should ideally be allowed to age several months before stripping. Exceeding the recommended film thickness will increase the tendency to cause asphalt lifting. Placing an inconspicuous test stripe to determine if a new asphalt surface has cured sufficiently to paint is recommended.

If it is necessary to paint new asphalt surfaces, do not exceed an application rate of 8 mils (200 microns) wet (approximately 200 sq ft/gal / 4.9 m<sup>2</sup>/L). Special care should be given to laps and edges of stencils to prevent excessive film thickness.

Asphalt surfaces generally require aging prior to painting.

If the asphalt is insufficiently cured, applying a thin coat (approximately 1/2 the recommended dft) generally reduces the extent of lifting and cracking.

Painted surfaces can become slippery when wet. Zone Marking paints are not intended for use as floor paints, and should not be used to paint large areas subject to pedestrian traffic. For instance, painting an entire traffic stall is not recommended.

Do not paint on wet surfaces.

Check adhesion by applying a test strip to determine the readiness for painting.

**Slip Resistance**

Some surfaces may require a slip resistant additive for safety. Add H&C SharkGrip® Slip Resistant Additive to the final coat applied following label directions. Sand may also be broadcast onto the wet paint or incorporated in the final coat. These additives should not be used in place of a non-skid finish.

**APPLICATION**

**Temperature:**  
 minimum 40°F / 4.5°C  
 maximum 110°F / 43°C  
 air, surface, and material  
 At least 5°F / 2.8°C above dew point  
**Relative humidity:** 85% maximum

The following is a guide. Changes in pressures and tip sizes may be needed for proper spray characteristics. Always purge spray equipment before use with listed reducer. Any reduction must be compatible with the existing environmental and application conditions.

**Reducer** Water  
 As needed up to 25% by volume

**Airless Spray Line Striper**  
 Pressure ..... 1800-2700 psi  
 Hose ..... 1/4" - 3/8" ID  
 Tip ..... .015" - .017"  
 Filter ..... 60 mesh

**Conventional Spray Line Striper**  
 Gun ..... Binks 21 (Bleeder)  
 Fluid Nozzle ..... #68  
 Air Nozzle ..... Internal mix, #709  
 Atomization Pressure ..... 45-80 psi  
 Fluid Pressure ..... 40-70 psi  
 NOTE: Fluid and atomization pressures are dependent on environmental conditions. Use the lowest pressures necessary to achieve a "flat line".

**Brush** Natural bristle  
**Roller Cover** 3/8" woven  
 with solvent resistant core

If specific application equipment is listed above, equivalent equipment may be substituted.

**CLEANUP INFORMATION**

Clean spills and spatters immediately with soap and warm water. Clean hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with VM&P Naphtha to prevent rusting of the equipment. Use VM&P Naphtha for overspray or dry paint clean up. Follow manufacturer's safety recommendations when using any solvent.

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin. The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.